

FLOORCOTE CONTRACT FINISH

PRODUCT DESCRIPTION

An alkyd based economical floor coating which is easy to apply and causes minimum reaction when applied over previously painted surfaces. Ideal for fast turnaround applications in factories and commercial areas requiring a hard wearing full gloss finish.

USES

Can be applied to most floor areas including workshops, offices, factory floors and warehouses where a cost effective finish is required.

TECHNICAL PROPERTIES

Colour	4 plus specials		
Finish	Full Gloss		
Curing Agent	n/a		
Mix Ratio	n/a		
Specific Gravity	0.96		
Volume Solids	44 ± 2%		
Recommended Film Thickness	80µm WFT / 35µm DFT		
Theoretical Spreading Rate	12 m ² /litre		
Application Method	Brush, Roller		
Flash Point	39°C		
VOC	430 g/litre		
Drying Times	10°C	20°C	30°C
Touch Dry	5 hours	3 hours	2 hours
Hard Dry	8 hours	5 hours	4 hours
Minimum Overcoat	16 hours	12 hours	10 hours
Maximum Overcoat	Indefinite	Indefinite	Indefinite
In Service Time	24 hours	24 hours	24 hours

CERTIFICATION/APPROVALS

RECOMMENDED SYSTEMS

Floorcote Rubberised Sealer, Floorcote Epoxy Sealer, Floorcote Etch Treatment, Floorcote Degreaser

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination.

On concrete, if well aged, thin first coat 10% with Thinner No.3

New concrete should be left at least 3 months before painting, then a moisture check carried out to ensure this lies within acceptable limits.

On previously painted surfaces, test a small area before full painting.

Unsound surfaces should be primed with Floorcote Rubberised Sealer.

Damp surfaces can be sealed with Floorcote Epoxy Sealer before applying paint.

Power floated concrete or granolithic surfaces should be 'opened' with Floorcote Etch Treatment.

Floorcote Degreaser is recommended for heavy dirt and grease contamination.

PRODUCT APPLICATION

Mixing

Stir thoroughly before use.

Thinners

Thinner No.3

Brush

Thin first coat with 10% Thinner No.3 and work well into surface. Apply a full second coat. If previously sealed with Floorcote Rubberised Sealer or Epoxy Sealer, apply two full coats. On previously painted surfaces, one full coat is usually sufficient to give full cover and even-ness.

Roller

Thin first coat with 10% Thinner No.3 and work well into surface. Apply a full second coat. If previously sealed with Floorcote Rubberised Sealer or Epoxy Sealer, apply two full coats. On previously painted surfaces, one full coat is usually sufficient to give full cover and even-ness.

Conventional Spray

Airless Spray

Air Assisted Airless Spray

Cleaner

Thinner No.3

Cleanup Considerations

All equipment should be cleaned immediately after use with Thinner No.3

It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied.

Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.

The user must observe local health, safety and environmental regulations when using this product.

Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

PACK SIZES

5 litre.

PACK WEIGHTS

5 litre: 4.8Kg.

STORAGE CONDITIONS

Store away from extremes of temperature.

LIMITATIONS

Do not apply below 5°C as drying will be affected. Ensure adequate ventilation and drying conditions prevail. Over-thick application should be avoided, this will extend drying period if use of area is required within 24 hours.

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.