

FLOORCOTE NON SKID DECK PAINT

PRODUCT DESCRIPTION

A modified alkyd based coating filled with aggregate to give a low profile, non-slip surface which is easily applied to areas where sure foot conditions are essential. The product has good drying characteristics, hence short down times and can be applied to most surfaces without major preparatory steps.

USES

Metal and wood deck areas of seagoing vessels, wet and slippery walkways and production environments, where minimum interruption can be tolerated.

TECHNICAL PROPERTIES

| | | | |
|-----------------------------------|------------------------------------|-------------|-------------|
| Colour | Cornflower, Red Oxide, Grey, Green | | |
| Finish | Rough/Matt | | |
| Curing Agent | n/a | | |
| Mix Ratio | n/a | | |
| Specific Gravity | 1.55 | | |
| Volume Solids | 75% | | |
| Recommended Film Thickness | 120µm WFT / 90µm DFT | | |
| Theoretical Spreading Rate | 8 m ² /litre | | |
| Application Method | Brush, Roller | | |
| Flash Point | 39°C | | |
| VOC | 195 g/litre | | |
| Drying Times | 10°C | 20°C | 30°C |
| Touch Dry | 5 hours | 3 hours | 2 hours |
| Hard Dry | 7 hours | 5 hours | 4 hours |
| Minimum Overcoat | 16 hours | 16 hours | 16 hours |
| Maximum Overcoat | See note* | See note* | See note* |

* Normally single coat application

CERTIFICATION/APPROVALS

RECOMMENDED SYSTEMS

Hi-Dur ZP Primer, Standard Wood Primer

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination. On metal and wood apply directly to previously painted surfaces, these should be abraded well to provide a good key. Any bare areas should be primed with Hi-Dur ZP Primer or Aluminium Wood Primer. Apply one full coat and leave to dry fully before use.

PRODUCT APPLICATION

| | |
|-----------------------------------|---|
| Mixing | Stir thoroughly before use and periodically during application to ensure aggregate remains consistently dispersed. |
| Thinners | Thinner No.3 |
| Brush | Apply one full coat unthinned. |
| Roller | Apply one full coat unthinned. |
| Conventional Spray | |
| Airless Spray | |
| Air Assisted Airless Spray | |
| Cleaner | Thinner No.3 |
| Cleanup Considerations | All equipment should be cleaned immediately after use with Thinner No.3 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations. |

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited. The user must observe local health, safety and environmental regulations when using this product. Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

PACK SIZES

5 litre

PACK WEIGHTS

5 litre: 7.75 Kg.

STORAGE CONDITIONS

Store away from extremes of temperature.

LIMITATIONS

Do not apply when RH exceeds 88% or the surface is less than 2°C above dew point. Drying will be affected in cold conditions. Adhesion will be affected if applied to damp surfaces.

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.