

STORMCOTE RUBBERISED SEALER

PRODUCT DESCRIPTION

A heavy duty chlorinated rubber sealer for the treatment of unsound surfaces such as masonry, cement, concrete, alkaline and dusty substrates to produce a tough, well bound base for subsequent masonry and other coatings. Penetrates deeply and has minimum effect on previous coatings which may be present.

USES

Exterior and interior masonry, chalky walls, ceilings and any location where serious surface degradation has occurred and required significant stabilisation.

TECHNICAL PROPERTIES

Colour	Clear		
Finish	Semi Gloss		
Curing Agent	n/a		
Mix Ratio	n/a		
Specific Gravity	1.00		
Volume Solids	35%		
Recommended Film Thickness	70µm WFT / 25µm DFT		
Theoretical Spreading Rate	14 m ² /litre (depends on surface porosity)		
Application Method	Brush, Roller, Spray		
Flash Point	23-31°C		
VOC	570 g/litre.		
Drying Times	10°C	20°C	30°C
Touch Dry	2 hours	1 hour	40 Minutes
Hard Dry	4 hours	2 hours	1 ½ hours
Minimum Overcoat	4 hours	2 hours	1 ½ hours
Maximum Overcoat	48 hours	48 hours	48 hours

CERTIFICATION/APPROVALS

RECOMMENDED SYSTEMS Stormcote range of products

SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination.

Friable surfaces should be scraped back to a sound base and unsound paint scraped back to a sound line.

Brush off loose dirt and dust.

Repair all cracks and holes with a suitable exterior filler.

Treat any algal or fungal growth with Stormcote Fungicidal Treatment.

PRODUCT APPLICATION

Mixing	Ready for use.
Thinners	-
Brush	Do not thin. Best applied by brush to ensure good penetration. Work well into the surface. Apply a second coat in severe cases. In less critical areas, these can be rolled.
Roller	Do not thin. Best applied by brush to ensure good penetration. Work well into the surface. Apply a second coat in severe cases. In less critical areas, these can be rolled.
Conventional Spray	Do not thin. Use in less critical areas. Use 35-45 psi pressure and 1.4-1.8 mm diameter nozzle.
Airless Spray	Do not thin. Use in less critical areas. Use tip 0.33-0.43 mm, 50-65° angle and 2000 psi pressure.
Cleaner	Thinner No.4
Cleanup Considerations	All equipment should be cleaned immediately after use with Thinner No.4 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.
The user must observe local health, safety and environmental regulations when using this product.
Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

PACK SIZES

5 litre

PACK WEIGHTS

5 litre: 5 kg.

STORAGE CONDITIONS

Store away from extremes of temperature.

LIMITATIONS

Ensure product is worked well into the surface by brush. Do not apply to damp surfaces or if there is a likelihood of rain.
This product will not repair major surface defects and all unsound and loose paint must be removed.

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.