

## STORMCOTE STABILISING SEALER

### PRODUCT DESCRIPTION

A heavy duty solvent based sealer for stabilising and bonding exterior and interior masonry and cement surfaces prior to application of masonry paint or other decorative coatings. Reduces porosity and provides a well bound, durable base with excellent alkali resistance. Available as a pigmented white version also.

### USES

Ideal for exterior or interior chalky or friable surfaces prior to application of masonry or decorative aqueous paints.

### TECHNICAL PROPERTIES

<b>Colour</b>	Clear or Semi Opaque White		
<b>Finish</b>	Semi Gloss		
<b>Curing Agent</b>	n/a		
<b>Mix Ratio</b>	n/a		
<b>Specific Gravity</b>	0.87		
<b>Volume Solids</b>	12%		
<b>Recommended Film Thickness</b>	85-170µm WFT / 10-20µm DFT		
<b>Theoretical Spreading Rate</b>	6-12 m <sup>2</sup> /litre		
<b>Application Method</b>	Brush, Roller, Spray		
<b>Flash Point</b>	39°C		
<b>VOC</b>	735 g/litre.		
<b>Drying Times</b>	<b>10°C</b>	<b>20°C</b>	<b>30°C</b>
Touch Dry	4 hours	2 hours	1 hour
Hard Dry	6 hours	3 hours	2 hours
Minimum Overcoat	6 hours	3 hours	2 hours
Maximum Overcoat	48 hours	48 hours	48 hours

### CERTIFICATION/APPROVALS

**RECOMMENDED SYSTEMS** Stormcote range of products

### SURFACE PREPARATION

Ensure surfaces are clean, dry and free from dirt, grease and other contamination.

Scrape back unsound areas and repair.

Treat any algal or fungal growth with Stormcote Fungicidal Treatment.

Apply one full coat and allow to dry before applying finish. In severe cases a second coat may be beneficial.

## PRODUCT APPLICATION

<b>Mixing</b>	Ready for use.
<b>Thinners</b>	-
<b>Brush</b>	Do not thin. Best applied by brush to ensure good penetration. Work well into the surface. Apply a second coat in severe cases. In less critical areas, these can be rolled.
<b>Roller</b>	Do not thin. Best applied by brush to ensure good penetration. Work well into the surface. Apply a second coat in severe cases. In less critical areas, these can be rolled.
<b>Conventional Spray</b>	Do not thin. Use in less critical areas. Use 35-45 psi pressure and 1.4-1.8 mm diameter nozzle.
<b>Airless Spray</b>	Do not thin. Use in less critical areas. Use tip 0.33-0.43 mm, 50-65° angle and 2000 psi pressure.
<b>Cleaner</b>	Thinner No.3
<b>Cleanup Considerations</b>	All equipment should be cleaned immediately after use with Thinner No.3 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

## HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited.  
The user must observe local health, safety and environmental regulations when using this product.  
Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

## PACK SIZES

5 litre

## PACK WEIGHTS

5 litre: 4.35 kg.

## STORAGE CONDITIONS

Store away from extremes of temperature.

## LIMITATIONS

Ensure product is worked well into the surface by brush.  
Do not apply to damp surfaces or if there is a likelihood of rain.  
This product will not repair major surface defects and all unsound and loose paint must be removed.

## DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.