

ACOTHANE MASTIC STANDARD GRADE

PRODUCT DESCRIPTION

Two component solvent-free mastic with excellent mechanical properties and low temperature curing characteristics.

USES

Repair of damaged coatings, filling of holes and cracks etc. prior to the application of finishing systems.

TECHNICAL PROPERTIES

Colour	Grey		
Finish			
Curing Agent	Acothane Activator		
Mix Ratio	3 Base : 1 Activator by volume		
Specific Gravity			
Volume Solids	100%		
Recommended Film Thickness	1-5 mm.		
Theoretical Spreading Rate	0.19 m ² per 250 g. @ 1 mm. thickness		
Application Method	Putty Knife, Spatula, Trowel, Brush		
Flash Point	200°C		
VOC	0 g/litre.		
Drying Times	10°C	20°C	30°C
Touch Dry		2 hours	
Hard Dry		8 hours	
Full Cure*		14 days	

*At low temperature curing rate will be slower.

CERTIFICATION/APPROVALS

BS6920: Part 1: 2000 "Specification" – Complying with the requirements for Water Regulations Advisory Scheme tests on water quality and is suitable for use with cold water

RECOMMENDED SYSTEMS

SURFACE PREPARATION

<u>Steel:</u>	Preferably grit blast to BS 7079 standard SA 2 ½. Surface profile 75-100 microns. Thorough abrading with wire brush, grinder, needle gun is acceptable.
<u>Overlap Area:</u>	Remove any loose material to establish a firm edge. Feather sound coating (inducing surface roughness). Thoroughly abrade to remove gloss, surface contaminants etc. by suitable method (sweep blasting, abrasive disk etc.).

PRODUCT APPLICATION

Mixing	Add Activator to Base and stir thoroughly. The use of a mechanical mixer is recommended. Pot life 12-15 mins. approx. @ 25°C.
Thinners	Do not thin.
Brush	Once mixed use immediately
Roller	
Conventional Spray	
Airless Spray	
Air Assisted Airless Spray	
Cleaner	Thinner No.4
Cleanup Considerations	All equipment should be cleaned immediately after use with Thinner No.4 It is advisable that equipment should be cleaned/flushed during the course of application, the frequency of which will depend on the volume of material used and timescale over which applied. Ensure all waste materials (including packaging) are disposed of in accordance with local regulations.

HEALTH, SAFETY & ENVIRONMENTAL

This product must be used in accordance with the Material Safety Data Sheet supplied by Spencer Coatings Limited. The user must observe local health, safety and environmental regulations when using this product. Consult Spencer Coatings Limited if there are any concerns over the suitability of this product.

PACK SIZES

PACK WEIGHTS

STORAGE CONDITIONS

Shelf life: 12 months

LIMITATIONS

Normal application requires relative humidity below 80%. To avoid risk of condensation application should be done only when the temperature of the steel surface is at least 3°C (5°F) higher than the dew point. Application at temperatures below 1°C (33°F) must be watched carefully since the possible presence of ice in the pores of the surface could result in poor adhesion and reduced corrosion protection.

Temperature: At Application: Preferably above 0°C (surfaces free from ice/ condensation)
In Service: Immersion 0 to 70°C depending on solution
Dry -20 to 120°C continuous

Notes:

- 1) Acothane UM Mastic is fully compatible with other Acothane grades.
- 2) UM Mastic Rapid can be used in operations requiring fast cure e.g. lay barge, weld coating and encapsulation of anode connectors, coating repair prior to trenching/backfilling. The standard grade material should be used for more leisurely coating operations.
- 3) UM Mastic has excellent adhesion to abraded F.B.E.

<u>TEST</u>	<u>SPECIFICATION</u>	<u>RESULT</u>
Bond Strength	DIN 53232 (Primed and Unprimed Steel)	15 N/mm ²
	DIN 53151 (Cross cut)	Glass G1
Water Vapour Permeability	DIN 52615	0.005 metric/perm.cm
Shrinkage	-	Negligible
Impact	ASTM 2794-69/14	20 N.M.
Tensile Strength	DIN 53504 13	20 N/mm ²
Elongation	ASTM D 2370	20-35%
Abrasion Resistance	ASTM 4060, CS17, 1 kg. load, 1000 cycles	<100 mg.
Shore Hardness	-	'D' 80 approx.
Flexibility	British Gas PS/CW6	Pass 2% strain @ 5°C
Cathodic Disbonding	British Gas GBE/CW6 (28 days @ 20°C) 1500 mV (calomel) 1.5 DFT Thickness	Pass

DISCLAIMER

The information given in these specifications and technical advice - whether verbal, or in writing or by way of trials is for guidance only and is given in good faith, but without warranty. This also applies where proprietary rights or third parties are involved. Any person using Spencer products without first making further enquiries as to the suitability of the products for the intended purpose and testing the products to assess their fitness for the purpose does so at their own risk. The application, use and processing of the products are beyond our control and are therefore your own responsibility, and we can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. The information contained in these data sheets is liable to modification from time to time in the light of experience and our policy of continuous development.

It is the user's responsibility to ensure that this sheet is current prior to using the product.